


# Encore RGP30r30

## Technical Data Sheet



**RGP r30** - Sustainable packaging film – Biaxially orientated polypropylene (BOPP) film co-extruded on both sides with polyolefinic copolymers



- Corona Treated Sealable Layer
- Oriented Polypropylene
- Sealable Layer

### Technical Features

- Heat-sealable on both sides
- Excellent water vapour barrier
- Anti-static protected
- Treated one side for laminating
- Puncture and impact-resistance maintained at low temperatures
- Unaffected by variations in climatic conditions

### Sustainable Features

- 30% Certified recycled content
- ISCC certified via mass balance
- Contributes to a Circular Economy
- Contributes to reducing the use of fossil resources

### Applications

- Overwrap
- VFFS
- HFFS
- Bag making

### Technical Properties (Typical Values)

Property	Test Method	Test Conditions	Units	RGP r30	
Thickness	Innovia Films test		micron	30	
			gauge	120	
Yield	Innovia Films test		m <sup>2</sup> /kg	36.6	
			in <sup>2</sup> /lb	25800	
			g/m <sup>2</sup>	27.3	
Permeability to: Water vapour	ASTM F 1249	38°C 90% RH 100°F 90% RH	g/m <sup>2</sup> .24 hrs	5.0	
			g/100in <sup>2</sup> .24 hrs	0.32	
Oxygen	ASTM F 1927	23°C 0% RH 73°F 0% RH	cc/m <sup>2</sup> .24 hrs	1600	
			g/100in <sup>2</sup> .24 hrs	103	
Optical: Gloss	ASTM D 2457	45°	units	85	
			Haze (wide angle)	ASTM D 1003	2.5°
Coefficient of friction (film to film)	ASTM D 1894	Static/ Dynamic		0.25-0.40	
Corona Treatment	Innovia Films Test		dynes/cm	38	
Tensile strength	ASTM D 882	Strain rate 50% / min	MN/m <sup>2</sup>	MD	230
				TD	192
			lb/in <sup>2</sup>	MD	33300
				TD	27500
Elongation at break	ASTM D 882	Strain rate 50% / min	%	MD	90
				TD	125
Elasticity modulus (1% secant)	ASTM D 882	Strain rate 10% / min	MN/m <sup>2</sup>	MD	2500
				TD	2100
			lb/in <sup>2</sup>	MD	361700
				TD	303800
Sealing Range	Innovia Films test	2 secs; 0.10MN/m <sup>2</sup> 2 secs; 15 psi	°C	115-145	
			°F	185-295	
				untreated to untreated	
Seal Strength	Innovia Films test	130°C; 2 secs; 0.10MN/m <sup>2</sup> 265°F; 2 secs; 15 psi	g(f)/25mm/in	>350 untreated to untreated	
Shrinkage	Innovia Films test	60 secs at 130°C (265°F)	%	MD	6.0
				TD	-1.0

MD Machine Direction TD Transverse Direction

All properties are tested under standard laboratory conditions: 23 ± 2°C, 50 ± 5% RH, (73 ± 4F, 50 ± 5% RH), unless otherwise stated. Where relevant, tests are based on international testing standards. Ref RGP r30 - 1 of 2 - 0222

# Encore RGP30r30

## Technical Data Sheet



### Reel Specifications

#### Nominal Reel Diameters

Film	Single Length (metres)	12x Length (metres)
RGP30r50	1250	15000

Film	Single Length (feet)	12x Length (feet)
RGP120r50	4100	49200

Other reel lengths are available in multiples of the single length as per the core diameter listed below.

Outside Diameter	1x	2x	4x	6x	8x	12x
For 77mm / 3in core	240mm 9½in	330mm 13in	450mm 18in	-	-	-
For 153mm / 6in core	-	-	475mm 18¾in	570mm 22½in	650mm 25½in	785mm 31in

### Corona Discharge Treatment

Encore RGP r30 is corona discharge treated on one side only, the reverse side exhibiting a low heat-seal threshold. The treated surface can be wound as either the inner or outer surface of Encore RGP r30. The treated surface is indicated by a symbol on a label attached to each reel.

Treated Surface	Ordering Code	Label Symbol
Inside	I	
Outside	O	

### Film Storage and Handling

No special conditions are required for the storage of Encore RGP r30 but it is recommended that dry conditions at temperatures below 30°C (85°F) are employed to minimise any deterioration of surface discharge treatment level. Encore RGP r30 is suitable for use for 6 months from the date of delivery and stocks should be used in rotation. Films should be allowed to reach operating room temperatures for 24 hours before use.

### Food Contact

Encore RGP r30 complies with the applicable EU and US legislation for most applications involving direct contact with foods. Full details are given on the Declaration of Compliance. Customers intending to use Encore RGP r30 in a food contact application should request a copy of this document from Innovia Films. Details of compliance with food contact legislation in non-EU countries are also available upon request.

### Health & Safety Guidelines

For Health & Safety information, please refer to literature reference B190.

**Disclaimer:** Innovia Films or any of its affiliated companies (hereinafter 'Innovia Films') declines any liability with respect to the use made by any third party of the information contained herein. The information contained herein represents Innovia Films' best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, the accuracy, the completeness or relevance of the data set out herein). Innovia Films is the sole owner or authorised user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted to the client's specific use. The client should perform his own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the client.

Ref RGP r30- 2 of 2 - 0222

#### Regional Offices:

Europe (UK) Tel +44 16973 42281  
Americas (USA) Tel +1 800 424 6273  
Asia-Pacific (Aus) Tel +61 3 9303 0600



[www.innoviafilms.com](http://www.innoviafilms.com)  
email: [packaging@innoviafilms.com](mailto:packaging@innoviafilms.com)  
™ Trademark of Innovia Films

