


Propafilm™ RSA

Technical Data Sheet

RSA - Transparent, Coextruded OPP film, with Shrink Properties.



Features

- Controlled shrink properties (approx. 10%)
- Two-side heat seal capability
- Anti-blocking and anti-static properties
- Excellent tear strength and puncture resistance
- Oil and grease resistant
- Meets FDA approval for use in food packaging applications
- Stable in varying conditions of humidity

Application

High speed wrapping of individual hard packs and cartons.

Technical Properties (Typical Values)

Property	Test Method	Test Conditions	Units	RSA		
Thickness	ASTM D 4321		micron	16	20	
			gauge	65	80	
Basis Weight	ASTM D 4321		g/m ²	15	18.2	
			lbs/ream	9.2	11.2	
Yield	ASTM D 4321		in ² /lb	46,900	38,700	
			m ² /kg	66.6	54.9	
Nominal Density	ASTM D 4321		g/m ³	0.91	0.91	
Tensile strength	Innovia test method	200mm/8"min	N/mm ²	MD	180	180
			N/mm ²	TD	290	290
			lbs/in ²	MD	26100	26100
			lbs/in ²	TD	42050	42050
Elongation at break	Innovia test method	200mm/8"min	%	MD	140	140
				TD	60	60
Coefficient of Friction	ASTM D 1894	Static / Dynamic		0.25	0.25	
MVTR	Innovia test method	38°C (100°F)/90% RH	g/m ² /day		6.0	6.0
			g/100in ² /day		0.39	0.39
Heat seal range	Innovia test method	Front 0.35N/ (0.5psi)/0.15secs	°C (min/max)		120-140	120-140
			°F (min/max)		248-284	248-284
Heat seal strength	Innovia test method	Front 140°C/0.35N/0.15secs 284°F/0.5PSI/0.15secs	N/15mm		1.5	1.8
			g/in		259	311
Shrinkage (production value)	Innovia test method	5min at 130°C (266°F)	%	MD	>10	>9
				TD	>10	>9

MD Machine Direction TD Transverse Direction

All properties are tested under standard laboratory conditions: 73 ± 4F, 50 ± 5% RH (23 ± 2°C, 50 ± 5% RH) unless otherwise stated. Where relevant, tests are based on international standards. This document is not a product specification and does not guarantee any specific product attributes. Any existing commercial rights or patents must be observed.

Propafilm™ RSA – 1 of 2 – 1019

Propafilm™ RSA

Technical Data Sheet

Nominal Reel Diameters

Film	Length (metres)	
RSA 16	4,000	5,219
RSA 20	3,200	4,266

Film	Length (feet)	
RSA 65	13,124	17,124
RSA 80	10,499	13,997

Outside Diameter	1x	3/4x
For 3in / 77mm core	12.0" (in) 300mm	13.75" (in) 350mm

All rolls are wound to length. Actual OD may vary with thickness and winding density variations.

Film Storage and Handling

This film is largely unaffected by climate influences, but it should be stored at temperatures below 100°F (38°C). The rolls should be kept in their original wrapping until used. After the rolls have been unwrapped, they should be stored upright with suitable protection for the edges. The films should be placed in the processing area 24 hours prior to processing to acclimatise. The films are largely unaffected by climatic conditions but should not be stored at temperatures above 104°F. Under suitable storage conditions the film can be stored for a period of six months without any risk of deterioration.

Food Contact

FDA approved for direct food contact. Please contact Technical Services for individual "original" FDA Food Contact statements.

Health & Safety Guidelines

MSDS sheets, as well as other product safety documents, are available for our films upon request.

Disclaimer: Innovia Films or any of its affiliated companies (hereinafter 'Innovia Films') declines any liability with respect to the use made by any third party of the information contained herein. The information contained herein represents Innovia Films' best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, the accuracy, the completeness or relevance of the data set out herein). Innovia Films is the sole owner or authorised user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted to the client's specific use. The client should perform his own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the client.

Propafilm™ RSA – 2 of 2 – 1019

Regional Offices:

Europe (UK) Tel +44 16973 42281

Americas (USA) Tel +1 800 424 6273

Asia-Pacific (Aus) Tel +61 3 9303 0600

www.innoviafilms.com

email: packaging@innoviafilms.com

™ Trademark of Innovia Films

