

Propacast™

Product Range
for Cast Polypropylene (CPP)
Films



packaging@innoviafilms.com

 **INNOVIA**

use our imagination...

High Puncture Resistance Films

Description	Film	Thickness micron	Yield		Seal Performance			
			m ² /kg	g/m ²	Threshold (°C) 2.0s dwell 0.10MN/m ²	Range (°C)		
				Metric	Metric			
Clear Heat sealable, puncture resistant and good tear properties	Propacast™ KB	20	55.56	18.00	120	30		
		25	44.44	22.50				
		30	37.04	27.00				
		35	31.75	31.50				
		40	27.78	36.00				
		45	24.69	40.50				
		50	22.22	45.00				
		55	20.20	49.50				
60	18.52	54.00						

Lamination Films

Clear Low temperature sealing film suitable for inner layers	Propacast™ KF	30	37.0	27.0	90	60
---	---------------	----	------	------	----	----

Freezer Applications

Clear Increased resistance to tear and puncture	Propacast™ KD	25	44.44	22.50	120	30
		30	37.04	27.00		
		40	27.78	36.00		
		50	22.22	45.00		

General Purpose Films

Clear Heat sealable	Propacast™ KG	20	55.56	18.00	120	30
		25	44.44	22.50		
		30	37.04	27.00		
		35	32.41	31.50		
		40	27.78	36.00		
		45	25.00	40.50		
		50	22.22	45.00		
		55	20.37	49.50		
		60	18.52	54.00		
		70	15.87	63.00		
90	12.35	81.00				
Clear Heat sealable	Propacast™ KL	20	55.56	18.00	120	30
		25	44.44	22.50		
		30	37.04	27.00		

Disclaimer: Innovia Films or any of its affiliated companies (hereinafter 'Innovia Films') declines any liability with respect to the use made by any third party of the information contained herein. The information contained herein represents Innovia Films' best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, the accuracy, the completeness or relevance of the data set out herein). Innovia Films is the sole owner or authorised user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted to the client's specific use. The client should perform his own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the client.

Ref C100 - 2 of 2 - 0222

Registered Offices:

Europe (UK) Tel +44 16973 42281
Americas (USA) Tel +1 800 424 6273
Asia-Pacific (Aus) Tel +61 3 9303 0600

www.innoviafilms.com
email: packaging@innoviafilms.com
™ Trademark of Innovia Films

