


Propafilm™ GLP (Tobacco)



Technical Datasheet

GLP - Printable High Speed Overwrapping Film with Shrink Tightening Properties.

Biaxially oriented polypropylene (BOPP) film co-extruded on both sides with heat-sealable polyolefinic copolymers.



- High Slip Sealable Layer
- Oriented Polypropylene Blend
- Corona Treated Low Slip Sealable Layer

Features

- Printable one side
- Superior controlled, balanced shrinkage
- Enhanced machine performance
- Satisfies requirements for vending blocking applications
- Excellent moisture and flavour barrier
- Differential slip properties for tight wraps
- Overcomes film relaxation problems
- Resistant to solvent attack

Applications

GLP is suitable for use in the tobacco industry for both high speed overwrapping of printed packs and display outers where exceptional pack appearances and wrap tightness are required.

PACK WRAP



CARTON WRAP



SHRINK



Technical Properties (Typical Values)

Property	Test Method	Test Conditions	Units	GLP		
Thickness	Innovia Films test		micron	18	20	25
			gauge	72	80	100
Yield	Innovia Films test		m ² /kg	61.0	54.9	44.0
			in ² /lb	42900	38600	31000
			g/m ²	16.4	18.2	22.7
Permeability to: Water vapour	ASTM F 1249	38°C 90% RH 100°F 90% RH	g/m ² .24 hrs g/100in ² . 24 hrs	6.8 0.44	6.0 0.39	4.1 0.26
Oxygen	ASTM F 1927	23°C 0% RH 73°F 0% RH	cc/m ² .24 hrs cc/100in ² . 24 hrs	1800 116	1500 97	1400 90
Optical: Gloss	ASTM D 2457	20°	units	130		
Haze (wide angle)	ASTM D 1003	2.5°	%	1.3		
Coefficient of friction (film to film)	ASTM D 1894	Static/ Dynamic		0.40 0.30		
Blocking	Innovia Films test	70°C (158°F) / 200g / 2hrs	N	6		
Tensile strength	ASTM D 882	Strain rate 50% / min	MN/m ²	MD	170	
			lb/in ²	TD	210	
Elongation at break	ASTM D 882	Strain rate 50% / min	%	MD	120	
				TD	80	
Elasticity modulus (1% secant)	ASTM D 882	Strain rate 10% / min	MN/m ²	MD	3000	
				TD	3600	
			lb/in ²	MD	435100	
				TD	522100	
Sealing range	Innovia Films test	2 secs; 0.10MN/m ² 2 secs; 15 psi	°C	110-140		
			°F	230-285		
Seal strength	Innovia Films test	109°C; 2 secs; 0.10MN/m ² 225°F; 2 secs; 15 psi	g(f)/25mm/ in	480		
Shrinkage	Innovia Films test	60 secs at 80°C (176°F) 60 secs at 120°C (248°F)	%	MD	3.7	
				TD	3.5	
			MD	7.0		
				TD	11.0	

MD Machine Direction TD Transverse Direction
All properties are tested under standard laboratory conditions: 23 ± 2°C, 50 ± 5% RH, (73 ± 4°F, 50 ± 5% RH), unless otherwise stated. Where relevant, tests are based on international testing standards.
Ref B294 - 1 of 2 - 0222

Propafilm™ GLP

Technical Data Sheet

Reel Specifications

Nominal Reel Diameters

Film	12x Length (metres)
GLP18	25200
GLP20	22800
GLP25	18000



Film	12x Length (feet)
GLP72	82680
GLP80	74803
GLP100	59055

Other reel lengths are available subject to negotiation.

Outside Diameter	2x	4x	6x	8x	12x
For 77mm / 3in core	-	450mm 18¼in	-	-	-
For 153mm / 6in core	-	475mm 19in	570mm 22¾in	650mm 26in	785mm 32in

Film Winding/Discharge Treatment

Discharge treatment is available on either the inner or outer surface of Propafilm™ GLP. The treated surface is identified by a symbol on a label as below.

Treated Surface	Ordering Code	Label Symbol
Inside	I	
Outside	O	

*For printing application consult an Innovia Films Technical Representative

Film Storage and Handling

No special conditions are required for the storage of Propafilm™ GLP but it is recommended that dry conditions at temperatures below 30°C (86°F) are employed. Propafilm™ GLP is suitable for use for 6 months from the date of delivery and stocks should be used in rotation. Films should be allowed to reach operating room temperatures for 24 hours before use.

Food Contact

Propafilm™ GLP complies with the applicable EU and US legislation for most applications involving direct contact with foods. Full details are given on the Declaration of Compliance. Customers intending to use Propafilm™ GLP in a food contact application should request a copy of this document from Innovia Films. Details of compliance with food contact legislation in non-EU countries are also available upon request.

Health & Safety Guidelines

For Health & Safety information, please refer to literature reference B190.

Disclaimer: Innovia Films or any of its affiliated companies (hereinafter 'Innovia Films') declines any liability with respect to the use made by any third party of the information contained herein. The information contained herein represents Innovia Films' best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, the accuracy, the completeness or relevance of the data set out herein). Innovia Films is the sole owner or authorised user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted to the client's specific use. The client should perform his own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the client.

Ref B294 – 2 of 2 – 0222

Regional Offices:

Europe (UK) Tel +44 16973 42281
Americas (USA) Tel +1 877 822 6273
Asia-Pacific (Aus) Tel +61 3 9303 0600

www.innoviafilms.com
email: tobacco@innoviafilms.com
™Trademark of Innovia Films

