


Propafilm™ AF

Technical Data Sheet

AF - Clear Biaxially oriented polypropylene (BOPP) film with antifog inside of the reel, both sides heat sealable, both sides corona treated.






- Treated Printable Heat Sealable Layer
- Transparent OPP Interlayer
- Transparent Specially Designed OPP Core
- Transparent OPP Interlayer
- Treated Heat Sealable Antifog Layer

Features

- Both sides corona treated
- Excellent antifog properties on inner side
- Excellent optical properties
- Good sealability

Applications

- For packaging fresh products
- Flexographic and rotogravure printing
- Laminations
- Horizontal and vertical packaging machines (HFFS-VFFS)



Technical Properties (Typical Values)

Property	Test Method	Test Conditions	Units	AF		
Thickness	ISO 4593		micron	25	30	35
Yield Unit weight	ISO 536		m ² /kg g/m ²	44.44 22.50	37.04 27.00	31.75 31.50
Density	ISO 845		g/cm ³	0.90		
Haze (wide angle)	ASTM D 1003	2.5°	%	2.0		
Coefficient of friction (inner/inner)	ISO 8295	Dynamic		0.30		
Corona treatment	ISO 8296		mN/m (dyne)	38/38		
Tensile Strength	ISO 527-1,-3		N/mm ²	MD TD	130 240	
Elongation at break	ISO 527-1,-3		%	MD TD	220 30	
Thermal shrinkage	Innovia Films test	120°C, 5'	%	MD TD	3.0 1.0	
Sealing range*	Innovia Films test	1"; 150N; 130°C	°C	105-140		
Heat seal strength (inner/inner)	Innovia Films test	1"; 150N; 130°C	N/15mm	3.5		

*The selection of sealing temperatures depends on the characteristic of heat sealing bars and packaging process speed.

MD Machine Direction TD Transverse Direction

All properties are tested under standard laboratory conditions: 23 ± 2°C, 50 ± 5% RH, unless otherwise stated. Where relevant, tests are based on international testing standards.

Propafilm™ AF - 1 of 2 - 0520

Propafilm™ AF

Technical Data Sheet

Reel Specifications

Nominal Reel Diameters

Film	Outside Diameter 570mm (metres) - core 152mm	Outside Diameter 770mm (metres) - core 152mm	Outside Diameter 980mm (metres) - core 152mm
AF25	9000	17000	27950
AF30	7500	14150	23300
AF35	6400	12150	19950

ns= non standard.

Other reel lengths are available subject to negotiation.

Reel Labelling

Different films have various special surfaces; these are indicated on the reel labels.

Film Storage and Handling

Recommended processing conditions: 15-35°C, humidity below 75% RH. Before processing it is recommended to season the film in the processing conditions at temperature 20°C for a minimum of 24 hours.

In case of transporting or storing the film:

- below +15°C or above +35°C seasoning time should be extended to 48 hours;
- below + 5°C or above +40°C seasoning time should be extended to 72 hours.

Compliance with the above guarantees correct film processing.

Food Contact

Propafilm™ AF complies with the applicable EU legislation for most applications involving direct contact with foods. Full details are given on the Declaration of Compliance. Customers intending to use Propafilm™ AF in a food contact application should request a copy of this document from Innovia Films. Details of compliance with food contact legislation in non-EU countries are also available upon request.

Health & Safety Guidelines

For Health & Safety information, please refer to Innovia Poland's Quality documents.

Disclaimer: Innovia Films or any of its affiliated companies (hereinafter 'Innovia Films') declines any liability with respect to the use made by any third party of the information contained herein. The information contained herein represents Innovia Films' best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, the accuracy, the completeness or relevance of the data set out herein). Innovia Films is the sole owner or authorised user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted to the client's specific use. The client should perform his own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the client.

Propafilm™ AF - 2 of 2 - 0520

Regional Offices:

Europe (UK) Tel +44 16973 42281

Americas (USA) Tel +1 800 424 6273

Asia-Pacific (Aus) Tel +61 3 9303 0600

www.innoviafilms.com

email: packaging@innoviafilms.com

™ Trademark of Innovia Films

