


# Propafilm™ MZS

## Technical Data Sheet

**MZS** - A reduced optical density metallised, coextruded OPP film, designed for cold seal applications



### Features

- Good cold seal adhesion
- Excellent adhesive and metal bond
- Reduced optical density for product density
- Excellent block resistance

### Application

- HFFS – Confectionery and Baked Goods
- High impact point-of-sale presentation
- Laminate to NHD 15
- Suitable for extrusion lamination



### Technical Properties (Typical Values)

Property	Test Method	Test Conditions	Units	MZS	
Thickness	Innovia test method		micron	15	
			gauge	60	
Yield	ASTM D 4321		in <sup>2</sup> /lb	51,600	
			m <sup>2</sup> /kg	73.3	
Basis Weight	ASTM D 4321		g/m <sup>2</sup>	13.7	
			lbs/ream	8.4	
Tensile strength	Innovia test method		kpsi	MD	20.3
				TD	43.5
Elongation at break	Innovia test method		%	MD	160
				TD	60
Optical density	Innovia test method			1.3	
MVTR	Innovia test method	38°C (100°F)/90% RH	g/m <sup>2</sup> /day	<0.80	
			g/100in <sup>2</sup> /day	<0.052	
OTR	Innovia test method		cc/m <sup>2</sup> /day	<175	
			cc/100in <sup>2</sup> /day	<11.3	

MD Machine Direction TD Transverse Direction

All properties are tested under standard laboratory conditions: 73 ± 4F, 50 ± 5% RH (23 ± 2°C, 50 ± 5% RH) unless otherwise stated. Where relevant, tests are based on international standards. This document is not a product specification and does not guarantee any specific product attributes. Any existing commercial rights or patents must be observed.

Propafilm™ MZS – 1 of 2 – 1019



*use our imagination...*

# Propafilm™ MZS

## Technical Data Sheet

### Conversion

Treatment and Winding	Surface Printing
Metal surface wound to outside of roll	Ink recommendations for all print processes are available
See roll tag about surface characteristics	Bump treatment of the metallised surface and application of a primer is recommended to optimize adhesion of surface inks or coatings. A protective top coat is suggested for applications with less than 100% ink coverage
	Polypropylene film characteristics are maintained for 6 months from the date of production except for metallised layer surface tension
	Excellent web flatness permits higher speed printing
	Run appropriate trials prior to production

#### Conversion Note -

Generally PVB or NC-based inks with adequate adhesion promoter are suitable for printing on this film. Drying temperatures should not exceed 170°F (76°C). Lowest possible web tension should be applied during conversion of this film. Usually laminated to Innovia Films' NHD using solvent-based, solvent-less adhesives or extrusion. Excellent sealing strength and anchorage with certain cold seal adhesives. Consult your coating supplier.

### Nominal Reel Diameters

Film	Length (metres)		
MZS 15	5,000	15,000	30,000

Film	Length (feet)		
MZS 60	16,404	49,213	98,425

Outside Diameter	1x	3x	6x
For 3in / 77mm core	13.1" (in) 333mm	-	-
For 6in / 153mm core	-	22.7" (in) 577mm	31.1" (in) 796mm

All rolls are wound to length. Actual OD may vary with thickness and winding density variations.

### Film Storage and Handling

The films should be placed in the processing area 24 hours prior to processing, to acclimatize. The films are largely unaffected by climatic conditions but should not be stored at temperatures above 104°F (40°C). Under suitable storage conditions, the film can be stored for a period of 6 months without any risk of deterioration.

### Food Contact

Propafilm™ MZS is FDA approved for food contact. Please contact Technical Services for other Food Contact statements.

### Health & Safety Guidelines

MSDS sheets, as well as other product safety documents, are available for our films upon request.

**Disclaimer:** Innovia Films or any of its affiliated companies (hereinafter 'Innovia Films') declines any liability with respect to the use made by any third party of the information contained herein. The information contained herein represents Innovia Films' best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, the accuracy, the completeness or relevance of the data set out herein). Innovia Films is the sole owner or authorised user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted to the client's specific use. The client should perform his own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the client.

Propafilm™ MZS – 2 of 2 –1019

#### Regional Offices:

Europe (UK) Tel +44 16973 42281  
 Americas (USA) Tel +1 800 424 6273  
 Asia-Pacific (Aus) Tel +61 3 9303 0600

[www.innoviafilms.com](http://www.innoviafilms.com)  
 email: [packaging@innoviafilms.com](mailto:packaging@innoviafilms.com)  
 ™ Trademark of Innovia Films

