


Propafilm™ NC

Technical Data Sheet

NC - Low Heat-Seal Threshold

Film. Biaxially oriented polypropylene (BOPP) film co-extruded on both sides with heat-sealable polyolefinic copolymers.



- Very Low Heat-Seal Threshold, Good Hot Slip Layer
- Oriented Polypropylene Blend
- Very Low Heat-Seal Threshold Layer

Features

- Heat-sealable both sides via low seal threshold coats
- Does not seal to coextruded films used in packet wrap provided recommended machine settings are used
- Good moisture and flavour barrier
- Optimised slip and anti-blocking both sides
- Strong seals for tamper evidence
- Very wide sealing range

Applications

NC are suitable for clear wrap/naked collation of wrapped packs where exceptional pack appearance is required.

Technical Properties (Typical Values)

Property	Test Method	Test Conditions	Units	NC	
Thickness	Innovia Films test		micron	23	25
			gauge	92	100
Yield	Innovia Films test		m ² /kg	47.8	44.0
			in ² /lb	33600	30900
			g/m ²	20.9	22.7
Permeability to: Water vapour	ASTM F 1249	38°C 90% RH 100°F 90% RH	g/m ² .24 hrs	5.3	5.0
			g/100in ² . 24 hrs	0.34	0.32
Oxygen	ASTM F 1927	23°C 0% RH 73°F 0% RH	cc/m ² .24 hrs	1650	1600
			cc/100in ² . 24 hrs	106	103
Optical: Gloss	BS 2923	20°	units	125	
Haze (wide angle)	ASTM D 1003	2.5°	%	1.5	
Coefficient of friction (out to out)	ASTM D 1894	Static/ Dynamic		0.30	
				0.25	
Tensile strength	ASTM D 882	Strain rate 50% / min	MN/m ²	MD	170
			lb/in ²	TD	210
Elongation at break	ASTM D 882	Strain rate 50% / min	%	MD	120
				TD	80
Elasticity modulus (1% secant)	ASTM D 882	Strain rate 10% / min	MN/m ²	MD	3000
				TD	3600
			lb/in ²	MD	435100
				TD	522100
Sealing range	Innovia Films test	2 secs; 0.10MN/m ² 2 secs; 15 psi	°C	90-140	
			°F	195-285	
Operational sealing range for clear wrap*	Innovia Films test	2 secs; 0.10MN/m ² 2 secs; 15 psi	°C	100-115	
			°F	210-240	
Seal strength	Innovia Films test	130°C; 2 secs; 0.10MN/m ² 265°F; 2 secs; 15 psi	g(f)/25mm/ in	500	
Shrinkage	Innovia Films test	60 secs at 120°C (250°F)	%	MD	4.5
				TD	3.5

MD Machine Direction TD Transverse Direction

All properties are tested under standard laboratory conditions: 23 ± 2°C, 50 ± 5% RH, (73 ± 4F, 50 ± 5% RH), unless otherwise stated. Where relevant, tests are based on international testing standards.

Ref B288 - 1 of 2 - 0320

Propafilm™ NC

Technical Data Sheet

Reel Specifications

Nominal Reel Diameters

Film	Length (metres)
NC23	3300
NC25	3000



Film	Length (feet)
NC92	10827
NC100	9843

Other reel lengths are available subject to negotiation.

Outside Diameter	
For 77mm / 3in core	330mm 13in
For 153mm / 6in core	355mm 14in

Film Winding

Propafilm™ NC has differential hot slip properties for maximum wrap tightness. When overwrapping, it is advised to use the low slip (higher coefficient of friction) surface on the inside of the wrap, against the wrapped packs. Propafilm™ NC is not recommended for printing applications.

Treated Surface	Ordering Code	Label Symbol
Inside	I	
Outside	O	

*For printing application consult an Innovia Films Technical Representative.

Film Storage and Handling

No special conditions are required for the storage of Propafilm™ NC but it is recommended that dry conditions at temperatures below 30°C (85°F) are employed. Propafilm™ NC is suitable for use for 6 months from the date of delivery and stocks should be used in rotation. Films should be allowed to reach operating room temperatures for 24 hours before use.

Food Contact

Propafilm™ NC complies with the applicable EU and US legislation for most applications involving direct contact with foods. Full details are given on the Declaration of Compliance. Customers intending to use Propafilm™ NC in a food contact application should request a copy of this document from Innovia Films. Details of compliance with food contact legislation in non-EU countries are also available upon request.

Health & Safety Guidelines

For Health & Safety information, please refer to literature reference B190.

Disclaimer: Innovia Films or any of its affiliated companies (hereinafter 'Innovia Films') declines any liability with respect to the use made by any third party of the information contained herein. The information contained herein represents Innovia Films' best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, the accuracy, the completeness or relevance of the data set out herein). Innovia Films is the sole owner or authorised user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted to the client's specific use. The client should perform his own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the client.

Ref B288 – 2 of 2 – 0320

Regional Offices:

Europe (UK) Tel +44 16973 42281
 Americas (USA) Tel +1 877 822 6273
 Asia-Pacific (Aus) Tel +61 3 9303 0600

www.innoviafilms.com
 email: tobacco@innoviafilms.com
 ™ Trademark of Innovia Films

