


Propafilm™ OLP

Technical Data Sheet

OLP - Barrier Coated Film.

Biaxially oriented polypropylene (BOPP) film coated on both sides with an aqueous dispersion of polyolefinic chloride (PVdC) copolymers.



- High Slip Sealable Layer
- Oriented Polypropylene Blend
- Corona Treated Low Slip Sealable Layer

Features

- Printable one side
- Superior controlled, balanced shrinkage
- Enhanced machine performance
- Satisfies requirements for vending blocking applications
- Excellent moisture and flavour barrier
- Differential slip properties for tight wraps
- Overcomes film relaxation
- Resistant to solvent attack

Applications

OLP20(80)/25(100) are suitable for use for both high speed overwrapping of printed packs and display outers where exceptional pack appearance and wrap tightness are required.

Technical Properties (Typical Values)

Property	Test Method	Test Conditions	Units	OLP	
Thickness	Innovia Films test		micron	20	25
			gauge	80	100
Yield	Innovia Films test		m ² /kg	54.9	44.0
			in ² /lb	38600	31000
			g/m ²	18.2	22.7
Permeability to: Water vapour	ASTM F 1249	38°C 90% RH 100°F 90% RH	g/m ² .24 hrs	6.0	4.1
			g/100in ² . 24 hrs	0.39	0.26
Oxygen	ASTM F 1927	23°C 0% RH 73°F 0% RH	cc/m ² .24 hrs	1500	1400
			cc/100in ² . 24 hrs	97	90
Optical: Gloss	ASTM D 2457	45°	units	130	
Haze (wide angle)	ASTM D 1003	2.5°	%	1.3	
Coefficient of friction (out to out)	ASTM D 1894	Static/ Dynamic		0.40	
				0.30	
Blocking	Innovia Films test	70°C / 158°F / 200g / 2hrs	N	6	
Tensile strength	ASTM D 882	Strain rate 50% / min	MN/m ²	MD	170
				TD	210
			lb/in ²	MD	24700
				TD	30500
Elongation at break	ASTM D 882	Strain rate 50% / min	%	MD	120
				TD	80
Elasticity modulus (1% secant)	ASTM D 882	Strain rate 10% / min	MN/m ²	MD	3000
				TD	3600
			lb/in ²	MD	435100
				TD	522100
Sealing range	Innovia Films test	2 secs; 0.10MN/m ² 2 secs; 15 psi	°C	110-140	
			°F	230-285	
Seal strength	Innovia Films test	109°C; 2 secs; 0.10MN/m ² 225°F; 2 secs; 15 psi	g(f)/25mm/ in	480	
Shrinkage	Innovia Films test	60 secs at 80°C (176°F) 60 secs at 120°C (248°F)	%	MD	3.7
				TD	3.5
				MD	7.0
				TD	11.0

MD Machine Direction TD Transverse Direction

All properties are tested under standard laboratory conditions: 23 ± 2°C, 50 ± 5% RH, (73 ± 4F, 50 ± 5% RH), unless otherwise stated. Where relevant, tests are based on international testing standards.

Ref B295 - 1 of 2 - 0719

Propafilm™ OLP

Technical Data Sheet

Reel Specifications

Nominal Reel Diameters



Film	Single Length (metres)	12x Length (metres)
OLP20	7600	22800
OLP25	6000	18000
Film	Single Length (feet)	12x Length (feet)
OLP80	24934	74803
OLP100	19685	59055

Outside Diameter	1x	2x	4x	6x	8x	12x
For 77mm / 3in core	-	-	450mm 18½in	-	-	-
For 153mm / 6in core	-	-	475mm 18¾in	570mm 22½in	650mm 25½in	785mm 31in

Other reel lengths are available subject to negotiation.

Film Winding/Discharge Treatment

Discharge treatment is available on either the inner or outer surface of Propafilm™ OLP. The treated surface is indicated by a symbol on a label attached to each reel.

Treated Surface	Ordering Code	Label Symbol
Inside	I	
Outside	O	

Film Storage and Handling

No special conditions are required for the storage of Propafilm™ OLP but it is recommended that dry conditions at temperatures below 30°C (85°F) are employed. Propafilm™ OLP is suitable for use for 6 months from the date of delivery and stocks should be used in rotation. Films should be allowed to reach operating room temperatures for 24 hours before use.

Food Contact

Propafilm™ OLP complies with the applicable EU and US legislation for most applications involving direct contact with foods. Full details are given on the Declaration of Compliance. Customers intending to use Propafilm™ OLP in a food contact application should request a copy of this document from Innovia Films. Details of compliance with food contact legislation in non-EU countries are also available upon request.

Health & Safety Guidelines

For Health & Safety information, please refer to literature reference B190.

Disclaimer: Innovia Films or any of its affiliated companies (hereinafter 'Innovia Films') declines any liability with respect to the use made by any third party of the information contained herein. The information contained herein represents Innovia Films' best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, the accuracy, the completeness or relevance of the data set out herein). Innovia Films is the sole owner or authorised user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted to the client's specific use. The client should perform his own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the client.

Ref B295 - 2 of 2 - 0719

Regional Offices:

Europe (UK) Tel +44 16973 42281

Americas (USA) Tel +1 800 424 6273

Asia-Pacific (Aus) Tel +61 3 9303 0600

www.innoviafilms.com

email: packaging@innoviafilms.com

™ Trademark of Innovia Films

