


RayoFloat™ APO-HS



Technical Data Sheet

Certified Recycling Code 5 PP by RecyClass

APO-HS - Low density high shrink polyolefin film for shrink sleeve labels and tamper evident applications.



Features

- Low density
- Suitable for floatation separation from PET during recycling processes
- Controlled TD shrinkage >70%
- High gloss
- High clarity
- Scuff resistant

Conversion

RayoFloat™ APO-HS is printable across a wide range of traditional flexographic and gravure processes. Exact inks should be recommended by your supplier.

Limonene is recommended as the preferred seaming solvent.



Technical Properties (Typical Values)

Property	Test Method	Test Conditions	Units	APO-HS
Thickness	Innovia Films test		micron	50
			gauge	200
Yield	Innovia Films test		m ² /kg	21.7
			in ² /lb	15255
Unit Weight			g/m ²	46.0
			lbs/ream	28.3
Haze (wide angle)	Innovia Films test	2.5°	%	7
Optical: Gloss	Innovia Films test	60°	%	120
Density	Innovia Films test		g/cm ³	0.92
Shrinkage	Innovia Films test	95°C, 10s	%	2
			MD	72
Tensile strength	ASTM D 882	Strain rate 50%/min	MN/m ²	18.7
			MD	230
Elongation at break	ASTM D 882	Strain rate 50%/min	%	250
			MD	36
Coefficient of friction	Innovia Films test		Treated side	0.47
			Non treated side	0.40

MD Machine Direction TD Transverse Direction

All properties are tested under standard laboratory conditions: 23 ± 2°C, 50 ± 5% RH, unless otherwise stated. Where relevant, tests are based on international testing standards.

RayoFloat™ APO-HS - 1 of 2 - 0723




use our imagination...

RayoFloat™ APO-HS

Technical Data Sheet

Conversion

The polyolefin outer layers can be solvent seamed with standard solvents. Suitable for both steam and hot air shrink tunnels



Reel Specifications

Nominal Reel Diameters

Film	Core Size/(mm)	Approx Outside Dia/(mm)	Length/(metres)
APO-HS50	152	730	7500
Film	Core Size/(in)	Approx Outside Dia/(in)	Length/(feet)
APO-HS200	6"	28.7"	24606

Alternative reel lengths are available subject to negotiation.

Film Storage and Handling

For RayoFloat™ APO, it is recommended that the film should be stored and transported at temperatures below 25°C. It is important these conditions are employed to minimise any changes to the films shrinkage properties. RayoFloat™ APO is suitable for use for 6 months from the date of delivery and stocks should be used in rotation.

Food Contact

RayoFloat™ APO-HS complies with the applicable EU and US legislation for most applications involving direct contact with foods. Full details are given on the Declaration of Compliance. Customers intending to use RayoFloat™ APO-HS in a food contact application should request a copy of this document from Innovia Films. Details of compliance with food contact legislation in non-EU countries are also available upon request.

Health & Safety Guidelines

For Health & Safety information, please refer to Innovia Poland's Quality documents.

Disclaimer: Innovia Films or any of its affiliated companies (hereinafter 'Innovia Films') declines any liability with respect to the use made by any third party of the information contained herein. The information contained herein represents Innovia Films' best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, the accuracy, the completeness or relevance of the data set out herein). Innovia Films is the sole owner or authorised user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted to the client's specific use. The client should perform his own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the client.

Regional Offices:

Europe (UK) Tel +44 16973 42281
Americas (USA) Tel +1 800 424 6273
Asia-Pacific (Aus) Tel +61 3 9303 0600

www.innoviafilms.com
email: labels@innoviafilms.com
™ Trademark of Innovia Films

