


RayoForm™ IW

Technical Data Sheet

IW - White Pigmented, Biaxially Oriented Polypropylene Film for In Mould Labelling.



Features

- Excellent whiteness
- Matt surface both sides
- Anti-static
- Recyclable with polyolefin materials
- Balanced biaxial orientation
- Suitable for sheet fed processes
- No 'orange peel' effect
- Resistant to moisture and oils

Printability

RayoForm™ IW can be printed by flexographic, gravure, letterpress and screen processes. Its anti-static nature also makes it ideally suited to sheet fed litho processes. However, exact ink systems should be recommended by your supplier. The matt nature of RayoForm™ IW make it ideally suited to sheet fed printing processes. Either surface of RayoForm™ IW can be printed.



Technical Properties (Typical Values)

Property	Test Method	Test Conditions	Units	IW	
Thickness	Innovia Films test		micron	58	72
			gauge	230	290
Yield	Innovia Films test		m ² /kg	17.6	14.2
			in ² /lb	12400	10000
			g/m ²	56.8	70.4
Optical opacity	ASTM D 2457	45°	%	80	83
Tensile strength	ASTM D 882	Strain rate 50%/min	MN/m ²	MD	175
				TD	155
			kpsi	MD	25.4
				TD	22.5
Elongation at break	ASTM D 882	Strain rate 50%/min	%	MD	85
				TD	110
Elasticity modulus (1% secant)	ASTM D 882	Strain rate 10%/min	MN/m ²	MD	2400
				TD	2100
			kpsi	MD	348
				TD	304
Dimensional stability	Innovia Films test	60 secs at 130°C (266°F)	%	MD	3.0
				TD	1.0

MD Machine Direction TD Transverse Direction

All properties are tested under standard laboratory conditions: 23 ± 2°C, 50 ± 5% RH, (73 ± 4F, 50 ± 5% RH), unless otherwise stated. Where relevant, tests are based on international testing standards.

RayoForm™ IW - 1 of 2 - 0520

RayoForm™ IW

Technical Data Sheet

Applications

RayoForm™ IW is a solid white, biaxially oriented polypropylene film for injection in mould labelling of polyethylene and polypropylene containers. Its balanced biaxial orientation makes it ideally suited to the complex die cut shapes required for multi-surface labelling of tubs as well as less demanding cylindrical mouldings. The films balanced orientation also results in reduced container distortion. The films solid nature ensures no 'orange peel' effect after moulding.

RayoForm™ IW72(290) is designed for labelling of large containers and durable goods.

Reel Specifications

Nominal Reel Diameters

Film	Single Length (metres)	12x Length (metres)
IW58	625	7500
IW72	530	6350
Film	Single Length (feet)	12x Length (feet)
IW230	2050	20500
IW290	1750	17500

Other reel lengths are available in multiples of the single length as per the core diameter listed below.

Outside Diameter	1x	2x	4x	6x	8x	12x
For 77mm / 3in core	240mm 9½in	330mm 13in	450mm 18in	-	-	-
For 153mm / 6in core	-	-	475mm 18¾in	570mm 22½in	650mm 25½in	785mm 31in

Alternative reel lengths/core sizes are available subject to negotiation.

Film Storage and Handling

For the storage of RayoForm™ IW it is recommended that dry conditions at temperatures below 30°C (86°F) are employed to minimise any deterioration of surface discharge treatment level. RayoForm™ IW is suitable for use for 6 months from the date of delivery and stocks should be used in rotation. Films should be allowed to reach operating room temperatures for 24 hours before use.

Food Contact

RayoForm™ IW complies with the applicable EU legislation for most applications involving direct contact with food. Details are given on the Declaration of Compliance. Customers intending to use RayoForm™ IW in a food contact application should request a copy of this document from Innovia Films.

Health & Safety Guidelines

For Health & Safety information, please refer to literature reference L190.

Disclaimer: Innovia Films or any of its affiliated companies (hereinafter 'Innovia Films') declines any liability with respect to the use made by any third party of the information contained herein. The information contained herein represents Innovia Films' best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, the accuracy, the completeness or relevance of the data set out herein). Innovia Films is the sole owner or authorised user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted to the client's specific use. The client should perform his own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the client.

RayoForm™ IW – 1 of 2 – 0520

Regional Offices:

Europe (UK) Tel +44 16973 42281

Americas (USA) Tel +1 877 822 6273

Asia-Pacific (Aus) Tel +61 3 9303 0600

www.innoviafilms.com

email: labels@innoviafilms.com

™ Trademark of Innovia Films

